



Catalogue Code	N.V (%)	Viscosity Cps/25°C	Modulus Kg/cm ²	Tensile Strength Kg/cm ²	Elongation %	Solvents	Characteristics	Applications
VPU/B - 1	35 ±1	60,000-90,000	5-10	40	700	DMF MEK TOL	Soft grade, high bonding strength with nylon	Garment
VPU/B - 2	35 ±1	50,000-80,000	35-40	400	400	DMF MEK TOL	High bonding strength	Hand Bags
VPU/B - 3	50 ±1	50,000-80,000	35-40	400	400	DMF MEK TOL	High solid content	Hand Bags
VPU/B - 4	35 ±1	60,000-80,000	5-10	40	650	DMF MEK TOL	Solvent Resistant	Garment
VPU/B - 5	35 ±1	60,000-90,000	8-10	100	850	DMF MEK TOL	Solvent Resistant	Garment
VPU/B - 6	40 ±1	60,000-100,000	30-35	450	700	DMF MEK	Soft grade	Garment
VPU/B - 7	45 ±1	80,000-100,000	8-10	90	1,200	DMF MEK TOL	Good adhesion with nylon	Garment
VPU/B - 8	50 ±1	10,000-20,000	50-60	150	500	DMF MEK TOL	Water pressure resistant	Garment

Please contact sales@vantaggio.us for more information and pricing
www.vantaggio.us

IMPORTANT: The descriptions, data and information supplied are presented in good faith and are believed to be correct and it is provided for your guidance only. Because many factors may affect processing or application and or use, we *strongly* recommend that before purchase and use of the product, that the buyer test the product in the particular application and or purpose under conditions expected during use to determine the suitability of the product for your particular application and or purpose. No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular application and or purpose or liabilities of consequential damage are made regarding products described, data or information expressed. In no case shall the descriptions, information, data provided be considered a part of our terms and conditions of sale. Further, it is understood that the buyer expressly understands and agrees that the descriptions, data, and information furnished by Vantaggio Chemical Co., LTD and or its agents or representatives hereunder given and assumes no obligation or liability for the description, data, and information given or results obtained, all such being given and accepted at your risk by accepting delivery of the product. Furthermore suggestions of product applications made by Vantaggio Chemical Co., LTD and or its agents or representatives are our opinion only, are given without payment and with no warranty expressed or implied of the results to be obtained.